



SGS IMME MONGOLIA LLC

### INSPECTION REPORT

Company : Darkhan Metallurgical Plant

Location: Darkhan Terminal

Date: 2024.3.26

Sample No:	Product weight	H <sub>2</sub> O	Fe	S	Al <sub>2</sub> O <sub>3</sub>	SiO <sub>2</sub>	TiO <sub>2</sub>	P	Number of Car:	
		ton	%	%	%	%	%	%		pcs
Lot33	1	872.40	0.12	58.87	4.23	1.22	5.50	0.11	0.02	10
	2	862.10	0.14	60.48	4.04	0.91	4.65	0.09	0.03	10
	3	950.60	0.01	59.58	3.66	1.03	5.13	0.15	0.02	10
	4	721.10	0.01	59.88	3.89	1.06	5.10	0.11	0.02	9
	5									
<b>Average result*</b>		<b>3,406.20</b>	<b>0.07</b>	<b>59.69</b>	<b>3.95</b>	<b>1.05</b>	<b>5.10</b>	<b>0.12</b>	<b>0.02</b>	<b>39</b>

NOTE: \*Average result of all analytes is for summary of product weight  
This result format of the inspection sample only for DMP's internal use only



Signature:

SGS-IMME Mongolia LLC